

1. DESCRIPTION

A water borne intumescent coating for the fire protection of structural steelwork.

2. PRODUCT FEATURES & RECOMMENDED USES

- Provides 120 minutes fire resistance to structural steel.
- Tested in accordance with BS 476: Part 21: 1987 and AS1530.4 by Warrington Fire Research and The Building Research Establishment.
- Highly competitive loadings for most steel section sizes, giving reduced application costs.
- Easy application properties.
- Minimal VOC's – EPA Compliant and 'environmentally friendly'.
- Topseals are not required in C1 interior environments. When using topseals please check compatibility with Promat before application.
- Recommended for on-site application. Off-site applications must be topcoated before being taken outside and should be handled carefully to avoid edge damage (see APPLICATION NOTES).
- Recommended for interior environments classified as C1 or C2 under the definitions in ISO 12944-2: 1998. For external application apply 2 coats of recommended Topseal.

3. VOLUME SOLIDS

68% ± 2%.

4. FILM THICKNESS

For example: WET MICRONS = 803~5275;
DRY MICRONS = 545~3550.

5. THEORETICAL COVERAGE

1.0 litre per m² at 680 microns (µm) dry or 1000 microns wet (1 0 0 0 microns = 1mm).

6. APPLICATION

Airless spray, brush, or roller.

7. DRYING TIMES*

At 650 microns DFT and RH 70%	10°C	20°C	25°C
Dust free	12 hours	4 hours	30 minutes
Hard dry	48 hours	24 hours	20 hours
Overcoating: Minimum Maximum	48 hours **	24 hours **	20 hours **

PRODUCTION NOTES

*Drying and overcoating times will vary with film thickness, temperature, relative humidity and ventilation. Do not apply below 5°C, temperature above 10°C preferred.

**Only overcoat with self or approved topseal, please consult Promat for advice. Maximum overcoating time is indefinite providing the surface is clean and the coating is sound. Coated surfaces must be kept in controlled, dry conditions until topsealed or degradation may occur.

APPLICATION NOTES

Method	Airless spray	Automatic spray	Conventional spray	Brush	Roller
Output fluid pressure	Minimum 3,000 psi	No	No	Yes	Yes
Tip size	21~25 thou				

Mix the paint thoroughly before use.

The information in this data sheet is correct at the time of printing. Consult Promat before applying as to the suitability for use otherwise we cannot be held responsible for conditions beyond our control.

Promat Asia Pacific Organisations

● AUSTRALIA +61 1800 30 20 20
● INDIA +91 (11) 2433 1594

● CHINA +86 (20) 8136 1167 / +86 (10) 8589 1254
● MALAYSIA +60 (3) 2095 8555

● SINGAPORE +65 6776 7635

● HONG KONG +852 2836 3692
● VIETNAM +84 (8) 931 5964

www.promat-ap.com

8. COLOURS

Off white.

9. FINISH

Matt.

10. POT LIFE AT 23°C

Not applicable.

11. PRODUCT WEIGHT

1.27 kg/litre.

12. STORAGE CONDITIONS

Store in dry, cool conditions and protect from frost.

13. MIXING RATIO

Not applicable.

14. THINNERS

Clean water.

15. SURFACE PREPARATION (STEEL)

Prior to application of the primer the steel must be cleaned to remove weld flux and general contamination in accordance with the primer manufacturers instructions. All sharp edges should be ground and weld spatter removed. Blast clean to AS 1627: Part 2: Swedish Standard SIS 05 59 00, or British Standard 7079 equivalent, as per primer manufacturers instructions. Apply compatible anti-corrosive primer in accordance with manufacturers written instructions to recommended DFT – Please consult Promat to confirm compatibility before application. Maximum 100 microns. Pay attention to edges of steel.

Consult relevant primer Product Data Sheets for further details. All primed surfaces should be clean, dry and free from all grease, oil and general contamination before coating.

16. HEALTH & SAFETY INFORMATION

Refer to Health & Safety Data Sheets. At all times observe precautionary notices on containers. For the Material Safety Data Sheet of PROMAPAIN[®]-H Intumescent Coating, please download the PDF from www.promat-ap.com/pdf/pmph_msds.pdf.

17. FLASH POINT

Not applicable.

18. EQUIPMENT CLEANER

Water.

Brush/roller application will typically give up to 500 microns dft for multi-coat application, but up to 1mm can be achieved with poor cosmetic finish. Highest standard of decorative finish is only likely to be achieved with careful airless spray application. Airless spray application will give up to 1600 microns dft in a single coat dependant on configuration. For an Architectural finish this thickness may have to be reduced to 1000microns dft depending up on the circumstances. Avoid exceeding maximum stated film thicknesses.

Off-site applications must be allowed sufficient hardening time before moving. Coated sections should be packed and handled so as to minimise damage to coating and prevent ponding by water, and should be stored and transported under cover. If possible, handling cleats should be attached to the steelwork to minimise lifting damage. Topseal must be applied before leaving the fabrication shop. On site, all damage should be repaired to original specification – consult Promat for advice. **Please consult Promat to confirm topseal compatibility before application.**

Only apply in conditions of good ventilation which should be maintained during drying. Do not apply when rain, mist, sleet or snow are imminent. Do not apply or allow to dry below 5°C, temperatures above 10°C are preferred. During application and drying time of the paint coating, the surface should be dry and the Relative Humidity should not exceed 90%, and as with all water borne coatings the RH should be maintained as low as possible. The steel temperature should remain at least 3°C above the dew point.

For latest information of the Promat Asia Pacific organisation contact details, please refer to www.promat-ap.com

ASIA PACIFIC HEADQUARTERS**Promat International (Asia Pacific) Ltd.**

Unit 19-02-01, Level 2 PNB Damansara
No.19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
MALAYSIA
Tel: +60 (3) 2095 5111
Fax: +60 (3) 2095 6111
Email: info@promat-ap.com

AUSTRALIA**Promat Australia Pty. Ltd.**

1 Scotland Road, Mile End South
Adelaide, SA 5031
Tel: +61 1800 30 20 20
Fax: +61 (8) 8352 1014
Email: mail@promat.com.au

New South Wales Office**Promat Australia Pty. Ltd.**

Unit 1, 175 Briens Road
Northmead, NSW 2152
Tel: +61 1800 30 20 20
Fax: +61 (2) 9630 0258
Email: mail@promat.com.au

Victoria Office**Promat Australia Pty. Ltd.**

3/273 Williamstown Road
Port Melbourne, VIC 3207
Tel: +61 1800 30 20 20
Fax: +61 (3) 9645 3844
Email: mail@promat.com.au

Western Australia Office**Promat Australia Pty. Ltd.**

Locked Bag 8
Subiaco, WA 6904
Tel: +61 1800 30 20 20
Fax: +61 1800 33 45 98
Email: mail@promat.com.au

CHINA**Promat China Ltd.**

Room 504, Block B, Qi Lin Plaza
13-35 Pan Fu Road
510180 Guangzhou
Tel: +86 (20) 8136 1167
Fax: +86 (20) 8136 1372
Email: info@promat.com.cn

Beijing Office**Promat North China**

(Division of Promat China Ltd.)
Room 1507 Building 5, SOHO Xiandaicheng
No.88 Jianguo Road, Chaoyang District
100022 Beijing
Tel: +86 (10) 8589 1254
Fax: +86 (10) 8589 2904
Email: info@promat.com.cn

HONG KONG**Promat International (Asia Pacific) Ltd.**

Room 1010, C.C. Wu Building
302-308 Hennessy Road
Wanchai
Tel: +852 2836 3692
Fax: +852 2834 4313
Email: apromath@promat.com.hk

INDIA**Promat International (Asia Pacific) Ltd.**

(India Representative Office)
S-4, Second Floor
B-87 Defence Colony
110024 New Delhi
Tel: +91 (11) 2433 1594 (general)
+91 (98) 1913 2398 (west area)
+91 (94) 4809 4050 (south area)
Fax: +91 (11) 2433 1595
Email: info-india@promat-asia.com

MALAYSIA**Promat (Malaysia) Sdn. Bhd.**


Unit 19-02-01, Level 2 PNB Damansara
No.19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
Tel: +60 (3) 2095 8555
Fax: +60 (3) 2095 2111
Email: info@promat.com.my

SINGAPORE**Promat Building System Pte. Ltd.**

10 Science Park Road, #03-14 The Alpha,
Singapore Science Park II
Singapore 117684
Tel: +65 6776 7635
Fax: +65 6776 7624
Email: info@promat.com.sg

VIETNAM**Promat International (Asia Pacific) Ltd.**

(Vietnam Representative Office)
Room 606 Giay Viet Plaza
180-182 Ly Chinh Thang Street
Ward 9, District 3, Hochiminh City
Tel: +84 (8) 931 5964 (south area)
+84 (4) 565 8101 (north area)
Fax: +84 (8) 931 5964 (south area)
+84 (4) 565 8677 (north area)
Email: phuong@promat-asia.com (south area)
trangoc@promat-asia.com (north area)

Your local Promat supplier

For Promat International groups worldwide: www.promat-international.com

1. This document is formulated on the basis of information and experience available at the time of preparation. Promat is constantly reviewing and up dating all of its test data and reserve the right to change specifications without notice.
2. Promat is not responsible if recipients of Fire test reports, assessments or literature incorrectly interpret their contents and use products based on those interpretations.